

PRODUCT DATA SHEET

Purolite® NRW700

Polystyrenic Gel, Type I Strong
Base Anion Resin, Hydroxide form,
Nuclear Grade

PRINCIPAL APPLICATIONS

- Steam Generator blowdown purification
- CVCS Deborating of Primary coolant
- Radwaste decontamination
- Mixed Bed anion component

ADVANTAGES

- High operating capacity
- Minimal residual chlorides and sulfates
- Minimal residual metals
- Low organic extractables and rinseables
- Highly converted to hydroxide form

SYSTEMS

- Make up water demineralizers
- Primary Coolant
- Radwaste

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	OH ⁻ form
Total Capacity	1.15 eq/L (25.1 Kgr/ft³) (OH ⁻ form)
Moisture Retention	42 - 47 % (Cl ⁻ form)
Particle Size Range	425 - 1200 µm
< 425 µm (max.)	2 %
Uniformity Coefficient (max.)	1.7
Conversion (min.)	95 % (OH ⁻ form)
Impurities Iron (max.)	50 ppm
Impurities Sodium (max.)	20 ppm
Impurities Heavy Metals (max.)	30 ppm
Anionic Form, CO ₃ ²⁻ (max.)	5 %
Anionic Form, SO ₄ ²⁻ (max.)	0.1 %
Anionic Form, Cl ⁻ (max.)	0.1 %
Specific Gravity	1.08
Shipping Weight (approx.)	680 - 715 g/L (42.5 - 44.7 lb/ft³)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F) (OH ⁻ form)
Temperature Limit, Regenerable Bed	60 °C (140.0 °F) (OH ⁻ form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com